## Quality Registration Technical specification

QR 0022 Created: 08/07/2013


# **Technical specifications**

# **CUBE** (Fixation Bracket clippable)



Finishing:								
Product	Number	Height	Width	Length	Dim A	Fmax	Unit	Packaging
		(mm)	(mm)	(mm)	(mm)	(kN)		(unit)
CUBE-SQ-110-PE	17186	0	0	0			ST	15

#### Mounting instructions:



### Load capacity:

Standard: IEC61537

Max. load:


P. 1 / 3 Rev01: 05/10/2017



# **Quality Registration** Technical specification

QR 0022 Created: 08/07/2013

Compatibility:



### Information:

Coupler:

Equipotential bonding: IEC61537

EC declaration: EC directive 2014/35/EU (Low voltage) as modified by directive 93/68/EEC (CE marking)

### Field of application according to resistance against corrosion:

Corrosion cla	sses according EN IS	SO 12994	ing.	· ·
Corrosion	Atmospheric			
class	corrosion	Indoor environment	Outdoor environment	Surface treatments
C1	<0,1μm	Heated buildings with neutral atmospheres: offices, shops, schools, hotels.		Electro-galvanised (EG) EN ISO 2081
C2	0,1 - 0,7μm	Unheated buildings where condensation may occur: sports halls, warehouses, shops.	Rural areas. Atmosphere with low impurities.	Pre-galvanised (PG) EN 10327 – EN 10143
сз	0,7 - 2μm	Production facilities with high moisture levels and some air impurities due to industrial processes: production plants.	City and industrial atmosphere, some impurities, coastal areas with low salt loads.	Dipped-galvanised (DG) EN ISO 1461
C4	2 - 4µm	Production facilities with high moisture levels and high air impurities due to industrial processes: swimming pools, Chemical industry.	Industrial areas and coastal areas with low salt load.	Dipped-galvanised (DG) EN ISO 1461 Polyester coating (CO) EN ISO 12944
C5-I	4 - 8μm	Polyester coating (CO)	Industrial areas with high moisture level and aggressive atmosphere.	Duplex (DU) (Dipped galvanised + Polyester coating) Stainless steel AISI 316L
C5-M	4 - 8μm	EN ISO 12944	Coastal or offshore areas with salt load.	Duplex (DU) (Dipped galvanised + Polyester coating)

P. 2/3 Rev01: 05/10/2017



## Quality Registration Technical specification

QR 0022 Created: 08/07/2013

#### Classification for resistance against corrosion according to IEC61537

Class	Reference- Material and Finish
0 (a)	None
1	Electroplated to a minimum thickness of 5 μm
2	Electroplated to a minimum thickness of 12 μm
3	Pre-galvanised to grade 275 to EN 10327 and EN 10326
4	Pre-galvanised to grade 350 to EN 10327 and EN 10326
5	Post-galvanised to a zinc mean coating thickness (minimum) of 45 μm according to ISO 1461 for zinc thickness only
6	Post-galvanised to a zinc mean coating thickness (minimum) of 55 μm according to ISO 1461 for zinc thickness only
7	Post-galvanised to a zinc mean coating thickness (minimum) of 70 μm according to ISO 1461 for zinc thickness only
8	Post-galvanised to a zinc mean coating thickness (minimum) of 85 μm according to ISO 1461 for zinc thickness only (usually high silicon steel)
9A	Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S30400 or EN 10088 grade 1-4301 without a post-treatment (b)
9B	Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S31603 or EN 10088 grade 1-4404 without a post-treatment (b)
9C	Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S30400 or EN 10088 grade 1-4301 with a post-treatment (b)
9D	Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S31603 or EN 10088 grade 1-4404 with a post-treatment (b)

<sup>(</sup>a) For materials which have no declared corrosion resistance classification.

P. 3 / 3 Rev01: 05/10/2017

 $_{(b)}$  The post-treatment process is used to improve the protection against crevice crack corrosion and the contamination by other steels.