
Quality Registration Technical specification

QR 0022 Created: 08/07/2013

Technical specifications

CLFI60-B90 (Bend CLFI60)



| Finishing: | Ultra galva | | | | | | | |
|--------------------|-------------|--------|-------|--------|-------|------|------|-----------|
| Product | Number | Height | Width | Length | Dim A | Fmax | Unit | Packaging |
| | | (mm) | (mm) | (mm) | (mm) | (kN) | | (unit) |
| CLFI60-B90-0200-UG | 18488 | 60 | 200 | 0 | 200 | | ST | 1 |
| CLFI60-B90-0300-UG | 18489 | 60 | 300 | 0 | 300 | | ST | 1 |
| CLFI60-B90-0400-UG | 18490 | 60 | 400 | 0 | 400 | | ST | 1 |
| CLFI60-B90-0500-UG | 18491 | 60 | 500 | 0 | 500 | | ST | 1 |
| CLFI60-B90-0600-UG | 18492 | 60 | 600 | 0 | 600 | | ST | 1 |

| Finishing: | Duplex | | | | | | | |
|--------------------|--------|--------|-------|--------|-------|------|------|-----------|
| Product | Number | Height | Width | Length | Dim A | Fmax | Unit | Packaging |
| | | (mm) | (mm) | (mm) | (mm) | (kN) | | (unit) |
| CLFI60-B90-0200-DU | 18667 | 60 | 200 | 0 | 200 | | ST | 1 |
| CLFI60-B90-0300-DU | 18668 | 60 | 300 | 0 | 300 | | ST | 1 |
| CLFI60-B90-0400-DU | 18669 | 60 | 400 | 0 | 400 | | ST | 1 |
| CLFI60-B90-0500-DU | 18670 | 60 | 500 | 0 | 500 | | ST | 1 |
| CLFI60-B90-0600-DU | 18671 | 60 | 600 | 0 | 600 | | ST | 1 |


Mounting instructions:

P. 1 / 4 Rev01: 05/10/2017



Quality Registration Technical specification

QR 0022 Created: 08/07/2013



Load capacity:

Standard: -

Max. load:

Load diagram: -

Information:

Coupler: BN08-16

Equipotential bonding: IEC61537

EC declaration: EC directive 2014/35/EU (Low voltage) as modified by directive 93/68/EEC (CE marking)

UG

ULTRA GALVA (UG)

is a high-performant metallic coating which offers an optimum surface protection in a wide variety of agressive and demanding environments, indoor as well as outdoor. The unique alloy of small amounts of magnesium and/or aluminium in the zinc bath provides ULTRA protection with a self-healing effect. Whilst zinc is essential for cathodic protection, magnesium prevents red rust. The passivation layer that comes on top, creates a seal that slows down the first traces of white rust.

ULTRA GALVA offers a number of advantages compared to the traditional hot dip finishing.

- the passivation layer offers a superior protection level. Hence, ULTRA GALVA, being cathodical, is self-healing in case of scratches, edges or perforations. Compared to hot dip, the articles remain very straight, no deflections appear nor flux or dull spots/ashes.
- ULTRA GALVA can conveniently be cold-processed without any risk on flakes because of the perfect adhesion of the coating to the metal.
- No zinc pins appear which enables one to install cables in a fast way avoiding any risk on damages to cables nor injuries of workers.
- Thanks to the longer life span, ULTRA GALVA does not require ongoing maintenance nor post painting actions.
- Three times less zinc is being applied compared to hot dip finishing. There is hence a lower impact on natural ressources as well as less pollution. On top, its production process generates less CO2 emission and ULTRA GALVA is 100% recyclable.

ULTRA GALVA is hence a vary valuable environmentally friendly alternative for the traditional stainless steel and hot-dip finishing!

וום

P. 2 / 4 Rev01: 05/10/2017



Quality Registration Technical specification

QR 0022 Created: 08/07/2013

Duplex coats DU

For applications where a very high corrosion resistance is required, such as the petrochemical industry or maritime applications, we advise our customers to use a duplex coating. A duplex coating is composed of a hot-dip galvanizing, followed by a powder coating (in two coats or one). Research has showed that galvanized parts with an (epoxy) powder coating, afford corrosion resistance that is up to 2.5 times higher than the sum of the wear life of both systems separately.

For example: the wear life of hot-dip galvanizing is 10 years while that of an epoxy coating is 5 years. So, in combination, this gives a wear life of up to 37 years. Usually, the added cost of a duplex coating is easily outweighed by the cost price of regularly recurring maintenance every few years. (see underneath `hot-dip galvanizing').

Field of application according to resistance against corrosion:

Corrosion classes according EN ISO 12994

| Corrosion | Atmospheric | | | |
|-----------|-------------|---|---|---|
| class | corrosion | Indoor environment | Outdoor environment | Surface treatments |
| C1 | <0,1μm | Heated buildings with neutral atmospheres: offices, shops, schools, hotels. | | Electro-galvanised (EG) EN ISO 2081 |
| C2 | 0,1 - 0,7μm | Unheated buildings where condensation may occur: sports halls, warehouses, shops. | Rural areas. Atmosphere with low impurities. | Pre-galvanised (PG) EN 10327 – EN 10143 |
| сз | 0,7 - 2μm | Production facilities with high moisture levels and some air impurities due to industrial processes: production plants. | City and industrial atmosphere, some impurities, coastal areas with low salt loads. | Dipped-galvanised (DG) EN ISO 1461 |
| C4 | 2 - 4µm | Production facilities with high moisture levels and high air impurities due to industrial processes: swimming pools, Chemical industry. | Industrial areas and coastal areas with low salt load. | Dipped-galvanised (DG) EN ISO 1461 Polyester coating (CO) EN ISO 12944 |
| C5-I | 4 - 8μm | Polyester coating (CO) | Industrial areas with high moisture level and aggressive atmosphere. | Duplex (DU) (Dipped galvanised + Polyester coating) Stainless steel AISI 316L |
| C5-M | 4 - 8μm | EN ISO 12944 | Coastal or offshore areas with salt load. | Duplex (DU) (Dipped galvanised + Polyester coating) |

P. 3 / 4 Rev01: 05/10/2017



Quality Registration Technical specification

QR 0022 Created: 08/07/2013

Classification for resistance against corrosion according to IEC61537

| Class | Reference- Material and Finish |
|-------|--|
| 0 (a) | None |
| 1 | Electroplated to a minimum thickness of 5 μm |
| 2 | Electroplated to a minimum thickness of 12 μm |
| 3 | Pre-galvanised to grade 275 to EN 10327 and EN 10326 |
| 4 | Pre-galvanised to grade 350 to EN 10327 and EN 10326 |
| 5 | Post-galvanised to a zinc mean coating thickness (minimum) of 45 μm according to ISO 1461 for zinc thickness only |
| 6 | Post-galvanised to a zinc mean coating thickness (minimum) of 55 μm according to ISO 1461 for zinc thickness only |
| 7 | Post-galvanised to a zinc mean coating thickness (minimum) of 70 μm according to ISO 1461 for zinc thickness only |
| 8 | Post-galvanised to a zinc mean coating thickness (minimum) of 85 μm according to ISO 1461 for zinc thickness only (usually high silicon steel) |
| 9A | Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S30400 or EN 10088 grade 1-4301 without a post-treatment (b) |
| 9B | Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S31603 or EN 10088 grade 1-4404 without a post-treatment (b) |
| 9C | Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S30400 or EN 10088 grade 1-4301 with a post-treatment (b) |
| 9D | Stainless steel manufactured to ASTM: A 240/A 240M – 95a designation S31603 or EN 10088 grade 1-4404 with a post-treatment (b) |

⁽a) For materials which have no declared corrosion resistance classification.

P. 4 / 4 Rev01: 05/10/2017

 $_{(b)}$ The post-treatment process is used to improve the protection against crevice crack corrosion and the contamination by other steels.